



ARENA SILICE IF 50/60

| MICRAS | Retenido % | Acumulado | |
|--------|------------|-----------|----------------------|
| 800 | 0,43 | 0,43 | |
| 630 | 1,42 | 1,85 | |
| 400 | 6,22 | 8,07 | |
| 315 | 13,37 | 21,44 | |
| 200 | 53,15 | 74,59 | |
| 160 | 16,3 | 90,89 | |
| 100 | 8,21 | 99,1 | |
| 80 | 0,58 | 99,68 | |
| 63 | 0,24 | 99,92 | <i>INDICE FINURA</i> |
| Fondo | 0,08 | 100 | 55 |



ANALISIS QUIMICO

| | |
|--------------------------------|---------|
| SiO ₂ | 98,20% |
| Al ₂ O ₃ | 1,00% |
| TiO ₂ | 0,17% |
| Fe ₂ O ₃ | 0,16% |
| CaO | 0,04% |
| MgO | 0,02% |
| Na ₂ O | <0,01 % |
| K ₂ O | 0,36% |
| P.p.calcinac. | 0,40% |