



ARENA SILICE IF 50/60

MICRAS	Retenido %	Acumulado	
800	0,43	0,43	
630	1,42	1,85	
400	6,22	8,07	
315	13,37	21,44	
200	53,15	74,59	
160	16,3	90,89	
100	8,21	99,1	
80	0,58	99,68	
63	0,24	99,92	<i>INDICE FINURA</i>
Fondo	0,08	100	55



ANALISIS QUIMICO

SiO ₂	98,20%
Al ₂ O ₃	1,00%
TiO ₂	0,17%
Fe ₂ O ₃	0,16%
CaO	0,04%
MgO	0,02%
Na ₂ O	<0,01 %
K ₂ O	0,36%
P.p.calcinac.	0,40%