



ARENA SILICE IF 60/70

MICRAS	Retenido %	Acumulado	
710	0,3	0,3	
500	1,4	1,7	
355	5,28	6,98	
250	26,22	33,2	
180	35,34	68,54	
125	22,85	91,39	
90	5,87	97,26	
63	2	99,26	INDICE FINURA
Fondo	0,74	100	66



ANALISIS QUIMICO

SiO ₂	96,80%
Al ₂ O ₃	1,50%
Fe ₂ O ₃	0,15%
MgO	0,04%
CaO	0,03%
Na ₂ O	0,06%
K ₂ O	0,69%
TiO ₂	0,25%
P.p. calcinac.	0,40%