



ARENA SILICE IF 80/100

MICRAS	Retenido %	Acumulado	
400	0,19	0,19	
315	2,17	2,36	
200	31,31	33,67	
160	25,99	59,66	
100	33,35	93,01	
80	4,29	97,3	
63	1,65	98,95	<i>INDICE FINURA</i>
Fondo	1,05	100	80



ANALISIS QUIMICO

SiO ₂	95,80%
Al ₂ O ₃	1,90%
TiO ₂	0,40%
Fe ₂ O ₃	0,21%
CaO	0,17%
MgO	0,07%
Na ₂ O	0,08%
K ₂ O	0,93%
P.p.calcinacion	0,50%